

Appl. No. 10/740,254  
Docket No. AA555C  
Notice of Non-Compliant Amendment dated February 6, 2007  
Reply to Notice of Non-Compliant Amendment mailed on February 15, 2007  
Customer No. 27752

RECEIVED  
CENTRAL FAX CENTER  
FEB 15 2007

### AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

#### Listing of Claims:

1. (Previously Presented) A polyol-in-silicone emulsion consisting essentially of:
  - (i) an alkyl dimethicone copolyol having an HLB of from about 4 to about 6, and a molecular weight of from about 10,000 to about 20,000, wherein the alkyl group is made of about 10 to about 22 carbons; and
  - (ii) a polyol, wherein the weight ratio of the alkyl dimethicone copolyol to the polyol is from about 100 : 1 to about 2 : 8;wherein said polyol-in-silicone emulsion consists essentially of said alkyl dimethicone copolyol and said polyol.
2. (Original) The polyol-in-silicone emulsion of claim 1, further comprising hydrophilic skin treatment agent in an amount soluble in the polyol.
3. (Previously Presented) A personal care composition comprising by weight:
  - (a) from about 0.01% to about 65% of the polyol-in-silicone emulsion according to Claim 1; and
  - (b) a carrier.
4. (Canceled)
5. (Canceled)
6. (Canceled)
7. (Canceled)
8. (Canceled)

Appl. No. 10/740,254  
Docket No. AA555C  
Notice of Non-Compliant Amendment dated February 6, 2007  
Reply to Notice of Non-Compliant Amendment mailed on February 15, 2007  
Customer No. 27752

9. (Original) The personal care composition of Claim 3 wherein the composition is an antiperspirant, wherein the carrier comprises a thickening agent, and an antiperspirant active.
10. (Original) A method of making the polyol-in-silicone emulsion according to Claim 1 comprising mixing the alkyl dimethicone copolyol with the polyol at a speed of at least about 1000 rpm and at a temperature of at least about 40°C.
11. (Original) A method of making the polyol-in-silicone emulsion according to Claim 2 comprising the steps of:
  - (a) mixing the polyol and the hydrophilic skin treatment agent; and
  - (b) mixing the alkyl dimethicone copolyol with the product of step (a) at a speed of at least about 1000 rpm and at a temperature of at least about 40°C.
12. (Canceled)
13. (Canceled)
14. (Canceled)